


Copper Wire

Hard and Soft Drawn Copper Wire on Spools



- UNS Designation Number: UNS C11000
- Nominal Chemicals: Copper 99.9%, Oxygen .04%
- Average Physical Properties: Hard Drawn: 49,000-67,000 psi, Soft Drawn: 36,000-40,000 psi
- Electrical Conductivity: 101% IACS (Soft), 99% IACS (Hard)
- Specifications: ASTM B 3

Gauge	Size	Ft/Lb	Lbs/Mft	1# Part Number	5# Part Number	10# Part Number	25# Part Number	50# Part Number	70# Part Number	75# Part Number	100# Part Number	200# Part Number
2	.258	4.980	201.000						150910			120494*
4	.204	6.280	126.000									150902
6	.162	12.580	79.500							120452*		150897
8	.129	20.000	50.000			513778	150889					
10	.102	31.800	31.400			498122	513786				150863	
12	.081	50.600	19.800	403290		101995						
14	.064	80.400	12.430	102072	102056	102030		150847				
16	.051	128.000	7.820	102111	102098	150839						
18	.040	203.000	4.920	102137		150821						
20	.032	323.000	3.090	102153	460242	150813	419380	506747				
22	.025	514.000	1.950	102179		150805						
24	.020	818.000	1.220	102195	498130	451552						
26	.016	1300.000	.770	102218		150782						
30	.010	3300.000	.303	272217								

Hard Temper Stocked in 200# Random Coils.

Soft Temper Stocked in 1#-50# Coils.

* Hard Drawn Temper, all others Soft Temper

Dimensions are in inches. All weights are approximate.

Sizes not shown may be available upon request.