


## Copper Sheet & Plate

### Sheet Copper - Standard Roofing Sizes



■ **Nominal Chemicals: Copper 99.5%, Oxygen .04%**

■ **Average Physical Properties:**

**Temper: Soft**                      **1/8 Hard**  
**Tensile: 34,000 psi**            **36,000 psi**  
**Hardness: F50**                    **F70**

■ **Electrical Conductivity: 101% IACS**

■ **Specifications: ASTM B 370, Temper Cold Rolled H00 (1/8 H) and 060 (Soft)**

Weight per Sq Ft		Thickness	Gauge	Size	Lbs/Sheet	Temper	Part Number
Ozs.	Lbs/Sq Ft						
12	.750	.0162	27	36 x 120	22.500	1/8 H	510233
16	1.000	.0216	24	36 x 96	24.000	1/8 H	142721
16	1.000	.0216	24	36 x 120	30.000	1/8 H	142713
16	1.000	.0216	24	48 X 96	32.000	1/8 H	142381
16	1.000	.0216	24	48 X 120	40.000	1/8 H	506399
20	1.250	.0270	22	36 x 96	30.000	1/8 H	142763
20	1.250	.0270	22	36 x 120	37.500	1/8 H	142755
20	1.250	.0270	22	48 x 120	50.000	1/8 H	492794
24	1.500	.0320	21	36 x 96	36.000	1/8 H	142789
24	1.500	.0320	21	36 x 120	45.000	1/8 H	142771
24	1.500	.0320	21	48 x 96	48.000	1/8 H	142399
24	1.500	.0320	21	48 x 120	60.000	1/8 H	421395
32	2.000	.0430	19	36 x 96	48.000	1/8 H	142810
32	2.000	.0430	19	36 x 120	60.000	1/8 H	431609
32	2.000	.0430	19	48 x 120	80.000	1/8 H	142404
48	3.000	.0647	16	36 x 96	72.000	1/8 H	142412
48	3.000	.0647	16	36 x 120	90.000	1/8 H	142420
48	3.000	.0647	16	48 x 120	120.000	1/8 H	142438

Dimensions are in inches. All weights are approximate.  
 Sizes not shown may be available upon request.

### Patterned Sheet Copper

Weight per Sq Ft		Thickness	Gauge	Size	Lbs/Sheet	Pattern	Part Number
Ozs.	Lbs/Sq Ft						
16	1.000	.0216	24	36 x 96	24.000	Barked	585602
16	1.000	.0216	24	36 x 96	24.000	Hammered	585597